


OFS Fitel, LLC Headquarters 2000 Northeast Expressway Norcross, GA 30071 USA Phone:+1 770.798.5555 Phone:+1 888.342.3743 [USA and Canada] Website: www.ofsoptics.com

Item # CF01493-12, 400 µm HCS 0.37 NA Low OH Optical Fiber

These fibers are ideally suited for use with both 650 and 850 nm active devices. For medical applications, they are USP Class VI non toxic, biocompatible and sterilizable. Part of the HCS fiber family, the 200 and 400 µm sized fibers are compatible with crimp and cleave termination.



Optical Properties | Dimensions/Geometric Properties | Coating/Buffer Descriptions | Mechanical and Testing Data | How To Order: | Applications For Any And/Or All Of These Products | Options

Optical Properties	
Туре	Multimode Step-Index
Numerical Aperture	0.37
Attenuation	@ 850 nm, ≤ 8 dB/km
Water Content	Low OH

Dimensions/Geometric Properties

Core Diameter	400 ± 8 μm
HCS® Cladding Diameter	430 +5 / -10 μm
ETFE Buffer Diameter	730 ± 30 μm
Core/Clad Offset	≤ 8 µm
Crimp & Cleave Compatible	Yes

Coating/Buffer Descriptions

Cladding Material	HCS
Buffer Material	ETFE
Operating Temperature	-65 to +125 °C

Mechanical and Testing Data

Short-Term Bend Radius	≥ 29 mm
Long-Term Bend Radius	≥ 47 mm
Proof Test Level	≥ 100 kpsi 0.689 GPa

How To Order:

Product Description Code	HCP-M0400T
Order From Location	AVON LOCATION 1.888.438.9936 toll-free in the United States and Canada 1.860.678.0371 from outside the U.S.A. 55 Darling Drive Avon, CT 06001, USA
Order By Item #	CF01493-12

Automotive Avionics Communications Electric Power Generation SCADA Systems High-Power Laser Delivery Illumination Industrial Automation / Control Laser Therapy and Surgery LED and Laser Source Coupling Medical lasers Near-IR Spectroscopy Nuclear Plasma Diagnostics Optical Pyrometry Semiconductor Equipment Sensing Short- to medium distance communications

Options

Buffer Color Buffer Diameter Buffer Material Proof Test